

Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ

Tel: 0161 975 9002 Email: sales@friedmans.co.uk Web: www.friedmans.co.uk

Technical Data Sheet

Article Life Power Recycled

Composition 78% POLYAMIDE (recycled)

22% ELASTANE

Weight m^2 (+/- 5%) 225 g/m² Weight linear m. (+/- 5%) 338 g/m lin. Total width (+/- 2%) 150 cm

Dimensional Stability – Washing 40° C width -5% MAX length -5% MAX

BS EN ISO 6330 @40°C - flat dry

Dimensional Stability – Steam width -3% MAX length -3% MAX

Resistance to pilling on fabric **5** on wool **3/4** NU Martindale – ISO 12945-2 7000 rotations

Hand Elongation (+/- 15%) width **105**% length **135**%

(min 89% - max 121%) (min 115% - max 155%)

Stretch to Dynamometer (+/- 15%)

INSTRON 3343 - 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm

Plain dyed width **100%** length **130%** (min 85% - max 115%) (min 111% - max 150%)

Modulus 40%
Plain dyed width 140-260g length 175-330g

Care labelling codes:



Recycled



Excellent UV
Protection



Ultra Chlorine Resistant



Excellent Coverage



AMAP

Sun Creams and Oil Resistant



Soft



Muscle Control

Shape

Retention



4 way Stretch



Perfect Fit



Eutro Constant



Pilling Resistar

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests.

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.