



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
 Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	Matt Nylon Lycra Flexcite	
Composition	80% POLYAMIDE 20% ELASTANE	
Weight m ² (+/- 5%)	170 g/m²	
Weight linear m. (+/- 5%)	255 g/m lin.	
Total width (+/- 2%)	150 cm	
Dimensional Stability – Washing 40° C BS EN ISO 6330 – flat dry	width -5% MAX	length -5% MAX
Dimensional Stability – Steam	width -4% MAX	length -4% MAX
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric 5	on wool 4/5
Hand Elongation (+/- 15%)	width 130% (min 110% - max 150%)	length 180% (min 153% - max 207%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 – 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm		
Plain dyed	width 120% (min 102% - max 138%)	length 170% (min 144% - max 196%)
<i>Modulus 40%</i> Plain dyed	width 100-160g	length 120-180g

Care labelling codes:



Ultra Chlorine Resistant



Excellent UV Protection



Perfect Fit



Pilling Resistant



Two Way Stretch



Resistance sun cream and oil

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.