



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
 Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	PF1019 Brisbane Polyester White	
Composition	82% POLYESTER 18% ELASTANE	
Weight m ² (+/- 5%)	190 g/m²	
Weight linear m. (+/- 5%)	285 g/m lin.	
Total width (+/- 2%)	150 cm	
Dimensional Stability – Washing 40° C BS EN ISO 6330	width -3% MAX	length -6% MAX
Dimensional Stability – Steam	width -3% MAX	length -5% MAX
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric 5	on wool 4/5
Hand Elongation (+/- 15%)	width 120% (min 102% - max 138%)	length 180% (min 153% - max 207%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 –load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm		
White for printing	width 110% (min 93% - max 126%)	length 160% (min 136% - max 184%)
<i>Modulus 40%</i> White for printing	width 110-190g	length 150-200g

Care labelling codes:



Pilling Resistant



Excellent UV Protection



Perfect Fit



Shape Retention



Two Way Stretch



Resistance to sun cream/oil



Ultra-Flat

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.