



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	Renew Wave	
Composition	91% POLYAMIDE (recycled) 9% ELASTANE	
Weight m ² (+/- 10%)	200 g/m²	
Weight linear m. (+/- 10%)	310 g/m lin.	
Total width (+/- 3%)	155 cm	
Dimensional Stability – Washing 40° C BS EN ISO 6330 – flat dry	width -5% MAX	length -5% MAX
– Steam	width -3% MAX	length -3% MAX
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric 4/5	on wool 1/2
Modulus 40%	width 45-80g	length 175-325g
Stretch to Dynamometer (+/- 10%) ZWICK - load 1,5 KG – strip test - size of the tested sample: 100 mm x 50 mm	width 110% (min 99% - max 121%)	length 75% (min 68% - max 83%)

Care labelling codes:



RECYCLED
YARN



TWO WAY STRETCH



UV PROTECTION



EXCELLENT COVERAGE

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.