



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
 Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	Silhouette Skin Flexcite (NOT RECOMMENDED FOR SWIMWEAR)	
Composition	88% POLYAMIDE 12% ELASTANE	
Weight m ² (+/- 5%)	140 g/m²	
Weight linear m. (+/- 5%)	210 g/m lin.	
Total width (+/- 2%)	150 cm	
Dimensional Stability – Washing 40° C BS EN ISO 6330 – flat dry	width -6% MAX	length -8% MAX
Dimensional Stability – Steam	width -4% MAX	length -6% MAX
Resistance to pilling NU Martindale – ISO 12945-2 7000 rotations	on fabric 5	on wool 2
Hand Elongation (+/- 15%)	width 160% (min 136% - max 184%)	length 160% (min 136% - max 184%)
Stretch to Dynamometer (+/- 15%) INSTRON 3343 – load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm.		
Plain dyed	width 150% (min 127% - max 172%)	length 150% (min 127% - max 172%)
<i>Modulus 40%</i> Plain dyed	width 20-70g	length 50-110g

Care labelling codes:



Perfect Fit



Two Way
Stretch



Soft

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.